



## Fire properties

Reaction to Fire		
Property	Value	According to
Reaction to Fire, Euroclass	A2 - s1, d0	EN 14303:2009 (EN 13501-1)

Other Fire Properties		
Property	Value	According to
Combustibility	Base product non-combustible	EN ISO 1182

## Thermal Properties

Thermal Resistance		
Property	Value	According to
Thermal Conductivity in 0 °C, $\lambda_0$	0,040 W/mK	EN 14303:2009+A1:2013 (EN 12667)
Thermal Conductivity in 10 °C, $\lambda_{10}$	0,040 W/mK	EN 14303:2009+A1:2013 (EN 12667)
Thermal Conductivity in 50 °C, $\lambda_{50}$	0,042 W/mK	EN 14303:2009+A1:2013 (EN 12667)
Thermal Conductivity in 100 °C, $\lambda_{100}$	0,046 W/mK	EN 14303:2009+A1:2013 (EN 12667)
Thermal Conductivity in 150 °C, $\lambda_{150}$	0,052 W/mK	EN 14303:2009+A1:2013 (EN 12667)
Thermal Conductivity in 200 °C, $\lambda_{200}$	0,060 W/mK	EN 14303:2009+A1:2013 (EN 12667)
Thermal Conductivity in 250 °C, $\lambda_{250}$	0,069 W/mK	EN 14303:2009+A1:2013 (EN 12667)
Dimensions and Tolerances	T5	EN 14303:2009+A1:2013

## Moisture Properties

Water Permeability		
Property	Value	According to
Water Absorption, Short Term WS, $W_p$	$\leq 1 \text{ kg/m}^2$	EN 14303:2009+A1:2013 (EN 1609)

Water Vapour Permeability		
Property	Value	According to
Water Vapour Diffusion Resistance	MV2	EN 14303:2009+A1:2013 (EN 12086)

## Mechanical Properties

Compressive Strength		
Property	Value	According to
Compressive stress at 10 % deformation CS(10), $\sigma_{10}$	$\geq 7$	

## Durability

Durability of Reaction to Fire Against Ageing/Degradation

The fire performance of mineral wool does not deteriorate with time. The Euroclass classification of product is related to the organic content, which cannot increase with time.

**Durability of Reaction to Fire Against High Temperature** The fire performance of mineral wool does not deteriorate with high temperature. The Euroclass classification of the product is related to the organic content, which remains constant or decreases with high temperature.

**Durability of Thermal Resistance Against Ageing/Degradation**

Thermal conductivity of mineral wool products does not change with time, experience has shown the fibre structure to be stable and the porosity contains no other gases than atmospheric air.

**Durability of thermal resistance against high temperature**

Thermal conductivity of mineral wool products does not change with time, experience has shown the fibre structure to be stable and the porosity contains no other gases than atmospheric air.

## Facings

**Facing Material**

Aluminium foil reinforced with a glass fibre net

Head Office: PAROC GROUP, P.O. Box 240 (Energiakuja 3), FI-00181 Helsinki, Finland, Tel. +358 46 876 8000, Fax +358 46 876 8002, [www.paroc.com](http://www.paroc.com)

The information in this brochure describes the conditions and technical properties of the disclosed products, valid at the time of publication of this document and until replaced by the next printed or digital version. The latest version of this brochure is always available on the Paroc website. Our information material presents applications for which the functions and technical properties of our products have been approved. However, the information does not mean a commercial guarantee. We do not assume liability of the use of third party components used in the application or the installation of our products. We cannot warrant the suitability of our products if used in an area or conditions which are not provided in our information material. As a result of constant further development of our products we reserve the right to make alterations to our information material at any time. PAROC is a registered trademark of Paroc Group. This data sheet is valid in following countries: United Kingdom.